

Product Class: Cork / Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	30.5 lbs./ft ³ (0.50 g/cm ³)
Tensile Strength	ASTM F152	120 lbs./in ² (827 kPa)
Compression @ 100 psi	ASTM F36	38%
Recovery		90%
Shore A Hardness	ASTM D2240	50
Flexibility	ASTM F147	3 max.
Fluid Immersion	ASTM F146	
	Oil 1 (70 hrs. at 212°F)	0 to +15%
	Oil 3 (70 hrs. at 212°F)	+10 to +30%
	Fuel A (22 hrs. at 74°F)	0 to +15%
Compression Set B	ASTM D395	
25% deflection, 22 hrs. at 158°F		90% max.
Temperature Range		- 40 to 250°F (- 40 to 121°C)

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

LNC01.RD.PSL.PS.0026
 8/9/2017
 W. Welch