

**Product Class: Composition Cork**

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	24 lbs./ft <sup>3</sup> (0.38 g/cm <sup>3</sup> )
Tensile Strength	ASTM F152	325 lbs./in <sup>2</sup> (2240 kPa)
Compression @ 100 psi	ASTM F36	19%
Recovery		83%
Flexibility	ASTM F147	2
Meets the following specs: ASTM F104 F214000RT MIL-G-12803 P2127A HH-C-576b, Class 3, Type II		
This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.		

*The values shown represent current production and may vary under different conditions.*