

**Product Class: Rubber**

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D297	51 lbs./ft <sup>3</sup> (0.82 g/cm <sup>3</sup> )
Tensile Strength	ASTM D412, Die C	100 lbs./in <sup>2</sup> (690 kPa)
Elongation	ASTM D412, Die C	80%
Tear Strength	ASTM D624, Die C	38 lbs./in. (6.7 N/mm)
Shore A Hardness	ASTM D2240	48
Flexibility	ASTM F147	1
Compression @ 100 psi	ASTM F36	25%
Recovery		92%
Compression Set B	ASTM D395	40% max.
25% deflection, 22 hrs. 158°F		

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

*The values shown represent current production and may vary under different conditions.*