

**Product Class: Cork / Rubber**

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	58 lbs./ft <sup>3</sup> (0.93 g/cm <sup>3</sup> )
Tensile Strength	ASTM F152	544 lbs./in <sup>2</sup> (3750 kPa)
Compression @ 400 psi	ASTM F36	21%
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	78
Compression Set B 25% deflection, 22 hrs. @ 158°F	ASTM D395	55% max
Coefficient of Friction	ASTM D4521	0.6
Temperature Range		- 40° to + 250°F (-40° to + 121°C)

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

*The values shown represent current production and may vary under different conditions.*

PS-130 711BNF (8020)  
 REV 103015  
 WMW