

Product Class: Cork / Rubber

<u>Property</u>	Test Method	Typical Result
Density	ASTM D3676	48.4 lbs./ft <sup>3</sup> (0.78 g/cm <sup>3</sup> )
Tensile Strength	ASTM F152	336 lbs./in <sup>2</sup> (2320 kPa)
Compression @ 300 psi	ASTM F36	25% (Recovery 95%)
@ 400 psi		32% (Recovery 83%)
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	65 to 75
Compression Set B 25% deflection, 22 hrs.		60% max
Fluid Immersion	ASTM F146	change in volume
Oil 1	70 hrs. @ 212°F	-2 to +20%
Oil 3	70 hrs. @ 212°F	+15 to +50%
Fuel A	22 hrs. @ 75°F	0 to +15%
Temperature Range	- 40° to + 250°F	(-40° to + 121°C)
Meets the following specs:	ASTM F104 F226000 M2 T MIL-G-12803 P2255A AMS-C-6183 (MIL-C-6183b)	Type I or II, Cl 2, Gr B

The values shown represent current production and may vary under different conditions.

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

PS-213 E40 (8016) REV 112015 WMW