



N-104 & DR-104

Product Class: Composition Cork

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	18.0 lbs./ft ³ (0.29 g/cm ³)
Tensile Strength	ASTM F152	175 lbs./in ² (1210 kPa)
Compression @ 100 psi	ASTM F36	28%
Recovery		85%
Flexibility	ASTM F147	5 max.
Meets the following specs: ASTM F104 F216000RT MIL-G-12803 P2127B HH-C-576b, Class 2, Type II		

This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

PS 188 N-104 & DR-104 (8036 & 8040)
REV 101015
WMW