



7619-II 7619NT-II

Product Class: Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D297	53 lbs./ft ³ (0.85 g/cm ³)
Tensile Strength	ASTM D412, Die C	190 lbs./in ² (1310 kPa)
Elongation	ASTM D412, Die C	95%
Tear Strength	ASTM D624, Die C	74 lbs./in. (13 N/mm)
Shore A Hardness	ASTM D2240	54
Flexibility	ASTM F147	1
Compression @ 100 psi	ASTM F36	17%
Recovery		91%
Compression Set B	ASTM D395	36%
25% deflection, 22 hrs. 158°F		
Coefficient of Friction	ASTM D4521	1.0

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

PS-165 7619-II & 7619NT-II (8023 & 8026)

REV 101015

WMW

715 Fountain Avenue, Lancaster, PA 17601 phone: 717.295.3400