



# FOREST RX ROLLS

## INSTALLATION AND MAINTENANCE MANUAL

Manufactured in the U.S.A. by:



Revised on 03/29/2018  
Supersedes all previous versions.  
Check website for updates and

## TABLE OF CONTENTS

### INSTALLATION

Job Site Conditions	3
Subfloors	3
Subfloor Preparation	3-5
Storage & Handling	5
Roll Installation	5-6
Heat Welding	6
Flash Coving Installation	7-8

### MAINTENANCE

Cleaning Procedures	9
Cleaning Product Chart	10

### WARRANTY

Warranty	11
----------	----

## INSTALLATION

### I. JOB SITE CONDITIONS

1. Installation should not begin until after all other trades are finished in the area. If the job requires other trades to work in the area after the installation of the floor, the floor should be protected with an appropriate cover. Kraft paper or plastic works well.
2. Areas to receive flooring should be weather tight and maintained at a minimum uniform temperature of 65°F (18°C) for 48 hours before, during, and after the installation.

### II. SUBFLOORS

1. Forest Rx may be installed over concrete, approved Portland- based patching and leveling materials, and wood.

**NOTE:** Gypsum-based patching and leveling compounds are not acceptable.

2. Wood Subfloors – Wood subfloors should be double construction with a minimum thickness of one inch. The floor must be rigid and free from movement with a minimum of 18 inches of well-ventilated air space below.
3. Underlayments – The preferred underlayment panel is American Plywood Association (APA) underlayment grade plywood, minimum thickness of 1/4-inch, with a fully sanded face.

**NOTE: Particleboard, chipboard, Masonite and lauan are not considered to be suitable underlayments.**

3. Concrete Floors – Concrete shall have a minimum compressive strength of 3000 psi. New concrete slabs should cure for a minimum of 28 days before installing Forest Rx. Concrete must be fully cured and permanently dry.

### III. SUBFLOOR REQUIREMENTS AND PREPARATION

1. Subfloors shall be dry, clean, smooth, level, and structurally sound. They should be free of dust, solvent, paint, wax, oil, grease, asphalt, sealers, curing and hardening compounds, alkaline salts, old adhesive residue, and other extraneous materials, according to ASTM F710.
2. Subfloors should be smooth to prevent irregularities, roughness, or other defects from telegraphing through the new flooring. The surface should be flat to the equivalent of 3/16" (4.8 mm) in 10' (3.0 m).
3. Mechanically remove all traces of old adhesives, paint, or other debris by scraping, sanding, or scarifying the substrate. Do not use solvents. All high spots shall be ground level and low spots filled with an approved Portland-based patching compound.
4. All saw cuts (control joints), cracks, indentations, and other non-moving joints in the concrete must be filled with an approved Portland-based patching compound.
5. Expansion joints in the concrete are designed to allow for expansion and contraction of the concrete. If a floor covering is installed over an expansion joint, it will likely fail in that area. Use expansion joint covers designed for resilient flooring.
6. Always allow patching materials to dry thoroughly and install according to the manufacturer's instructions. Excessive moisture in patching material may cause bonding problems or a bubbling reaction with the E-Grip™ III adhesive.

## INSTALLATION

### HAZARDS:

**SILICA WARNING**– Concrete, floor patching compounds, toppings, and leveling compounds can contain free crystalline silica. Cutting, sawing, grinding, or drilling can produce respirable crystalline silica (particles 1-10 micrometers). Classified by OSHA as an IA carcinogen, respirable silica is known to cause silicosis and other respiratory diseases. Avoid actions that may cause dust to become airborne. Use local or general ventilation or provide protective equipment to reduce exposure to below the applicable exposure limits.

**ASBESTOS WARNING** – Resilient flooring, backing, lining felt, paint, or asphaltic “cutback” adhesives can contain asbestos fibers. Avoid actions that cause dust to become airborne. Do not sand, dry sweep, dry scrape, drill, saw, beadblast, or mechanically chip or pulverize. Regulations may require that the material be tested to determine the asbestos content. Consult the document “Recommended Work Practices for Removal of Existing Resilient Floor Coverings” available from the Resilient Floor Covering Institute.

**LEAD WARNING** – Certain paints can contain lead. Exposure to excessive amounts of lead dust presents a health hazard. Refer to applicable federal, state, and local laws and the publication “Lead Based Paint: Guidelines for Hazard Identification and Abatement in Public and Indian Housing” available from the United States Department of Housing and Urban Development.

7. Moisture must be measured using the RH Relative Humidity test method per ASTM F2170 standard. Moisture content should not exceed 85% RH. If the levels exceed the limitations, the installation should not proceed until the situation has been corrected.
8. In the event that a moisture mitigation system is required, it must conform to the ASTM F3010 Standard Practice for Two-Component Resin Based Membrane Forming Moisture Mitigation Systems for use Under Resilient Floor Coverings.
9. It is essential that pH tests be taken on all concrete floors. If the pH is greater than 9, it must be neutralized prior to beginning the installation.
10. Adhesive bond tests should be conducted in several locations throughout the area. Glue down 3' x 3' test pieces of the flooring with the recommended adhesive and trowel. Allow to set for 72 hours before attempting to remove. A sufficient amount of force should be required to remove the flooring and, when removed, there should be adhesive residue on the subfloor and on the back of the test pieces.
11. It is essential that pH tests be taken on all concrete floors. If the pH is greater than 9, it must be neutralized prior to beginning the installation.
12. Adhesive bond tests should be conducted in several locations throughout the area. Glue down 3' x 3' pieces of the flooring with the recommended adhesive and trowel. Allow to set for 72 hours before attempting to remove. A sufficient amount of force should be required to remove the flooring, and there should be adhesive on the subfloor and the back of the flooring.
13. It is essential that pH tests be taken on all concrete floors. If the pH is greater than 9, it must be neutralized prior to beginning the installation.
14. Adhesive bond tests should be conducted in several locations throughout the area. Glue down 3' x 3' test pieces of the flooring with the recommended adhesive and trowel. Allow to set for 72 hours before attempting to remove. A sufficient amount of force should be required to remove the flooring and, when removed, there should be adhesive residue on the subfloor and on the back of the test pieces.

## INSTALLATION

### IV. MATERIAL STORAGE AND HANDLING

1. Material should be delivered to the job site in its original, unopened packaging with all labels intact.
2. Roll material should always be stored on end. Storing Forest Rx laying down may cause wetting, which causes permanent memory of the material. Rolls should only be stored on a clean, dry, smooth surface.
3. Inspect all materials for visual defects before beginning the installation. No labor claim will be honored on material installed with visual defects. Verify the material delivered is the correct style, color, and amount. Any discrepancies must be reported immediately before beginning installation.
4. The material and adhesive must be acclimated at room temperature for a minimum of 48 hours before starting installation.
5. All Forest Rx rolls must be unrolled and installed in the same direction. Laying rolls in the opposite direction can cause color variations between the rolls.




Diagram 1

6. Lay the rolls to provide as few seams as possible with economical use of materials. Match edges for color shading and pattern at seams. Be prepared to straight edge cut the side seams to ensure pattern consistency. For best results, the installer should unroll all rolls and allow to relax overnight.

**NOTE:** When handling or installing Forest Rx, special care should be taken not to sharply fold or crease the material. This can result in permanent visual damage to the PUR wear layer which is not covered under Ecore's product warranty.

### V. INSTALLATION – Forest Rx ROLL MATERIAL

1. Make the assumption that the walls you are butting against are not straight or square. Using a chalk line, make a starting point for an edge of the flooring to follow. The chalk line should be set where the first seam will be located.
2. Remove the Forest Rx from the shrink wrap and unroll it onto the floor. Lay the vinyl on the floor in a way that will use your cuts efficiently. Cut all rolls at the required length, including enough to run up the wall a couple inches.
3. If end seams are necessary, they should be staggered on the floor and overlapped approximately 2". End seams will be trimmed after acclimation period using a square to ensure they fit tightly without gaps. Match and cut seams to maintain overall continuity of color and pattern.
4. After allowing proper acclimation and rough cuts are made you may begin the installation.
5. Align the first edge to the chalk line. It is very important that the first seam is perfectly straight.
6. Position the second roll with appropriate overlap required to maintain board pattern consistency. After seams are trimmed, the edges should fit snug with no visual gaps. Care should be taken to not over compress the seam. Over compressed seams will cause peaking.
7. Repeat for each consecutive sheet necessary to complete the area or those rolls that will be installed that day.

## INSTALLATION

### VI. INSTALLATION – Adhesive Application

1. After performing the above procedures, begin the application of the adhesive. We recommend E-Grip III, a one-component moisture-cured polyurethane adhesive. E-Grip III should not be mixed. It is specially formulated for use right out of the pail. Apply E-Grip III to the substrate using a 1/16" square-notched trowel.
2. Fold over the first drop along the wall (half the width of the roll). Rolls are 6 feet wide and 30 feet long. When roll is folded over this will leave an exposed area of substrate that is 3 feet wide and 30 feet long.
3. Spread the adhesive using the proper size square-notched trowel. Take care not to spread more E-Grip III than can be covered with flooring within 30 minutes. The open time of the adhesive is 30–40 minutes at 70°F and 50% relative humidity.

**NOTE:** Temperature and humidity affect the open time of the adhesive. Temperatures above 70°F and/or relative humidity above 50% will cause the adhesive to set up more quickly. Temperatures below 70°F and/or relative humidity below 50% will cause the adhesive to set up more slowly. The installer should monitor the on-site conditions and adjust the open time accordingly.

4. Lay the flooring into the wet adhesive. Do not allow the material to “flop” into place; this may cause air entrapment and bubbles beneath the flooring.
5. Immediately roll the floor with a 75–100 lb. roller to ensure proper adhesive transfer. Overlap each pass of the roller by 50% of the previous pass to ensure the floor is properly rolled. Roll the width first and then the length.
6. Fold over the second half of the first roll and half the width of the second roll. Taking roll sizes into account, this will provide an exposed area of substrate of 6 feet wide and 30 feet in length per roll. Spread the adhesive, roll the flooring, and repeat for each consecutive drop.
7. Continue the process for each consecutive drop. Work at a pace so that you are always folding material back into wet adhesive bed.

**NOTE:** Never leave adhesive ridges or puddles. They will telegraph through the material.

8. Do not allow E-Grip III to cure on your hands or the flooring. Immediately wipe off excess adhesive with a rag dampened with mineral spirits! Cured adhesive is very difficult to remove from hands. We strongly suggest wearing gloves while using E-Grip III.
9. Hand roll all seams after the entire floor has been rolled.
10. Keep traffic off the floor for a minimum of 24 hours. Floor should be free from rolling loads for a minimum of 72 hours.

### VII. INSTALLATION – Heat Welding Forest Rx Rolls

1. Groove seams in sheet flooring as required, and heat weld with manufacturers welding rod.
2. All seams must be heat welded. Prior to the two part skiving process, mix a solution of 1 part mild dish soap to 10 parts of cold water. Apply the liquid soap solution over a 4" wide area of the welded seam prior to skiving the first pass. This will allow for a smoother seam and help avoid scuffing or scratching of the rubber floor surface.
3. After the first pass, allow the weld rod to cool down for 10 to 20 minutes prior to re-application of the soapy liquid and final skive. For best results, use a Mozart Skive Knife to trim/skive the cold weld rod.


## INSTALLATION

### VIII. INSTALLATION – Flash Coving Procedures Forest Rx Rolls

1. Remove the Forest Rx from the shrink wrap and unroll it onto the floor. Lay the material on the floor in a way that will use your cuts efficiently. Cut all rolls at the required length.
2. If end seams are necessary, they should be staggered on the floor and overlapped approximately 2". End seams will be trimmed after acclimation period using a square to ensure they fit tightly without gaps.
3. After allowing proper acclimation and rough cuts are made you may begin the installation.
4. Note: it is very important that the first seam is perfectly straight.
5. Position the second roll so it is snug with the adjacent roll, but not compressed. After seams are trimmed, if necessary, the edges should fit snug with no visual gaps. Care should be taken to not over compress the seam. Over compressed seams will cause peaking.
6. Repeat for each consecutive sheet necessary to complete the area or those rolls that will be installed that day.
7. After the rolls are rough fitted for the room strike chalk lines 4" from the walls for flash coving.
8. Where the outline for the seam is marked make square cut with a fixed straight blade utility knife, this will prepare the edge for the picture frame flash cove installation.
9. Prepare the 5mm rubber underlayment 4" strip to be installed between the wall and the prepared edge of the Vinyl.
10. After performing the above procedures, begin the application of the adhesive. We recommend E-Grip III, a one-component moisture-cured polyurethane adhesive. E-Grip III should not be mixed. It is specially formulated for use right out of the pail. Apply E-Grip III to the substrate using a 1/16" square-notched trowel.
11. Fold over the first drop along the wall (half the width of the roll). Remove the 5mm rubber underlayment and set aside. Rolls are 6 feet wide and 30 feet long. When roll is folded over this will leave an exposed area of substrate that is 3 feet wide and 30 feet long.
12. Spread the adhesive using the proper size square-notched trowel. Take care not to spread more E-Grip III than can be covered with flooring within 30 minutes. The open time of the adhesive is 30–40 minutes at 70°F and 50% relative humidity. NOTE: Temperature and humidity affect the open time of the adhesive. Temperatures above 70°F and/or relative humidity above 50% will cause the adhesive to set up more quickly. Temperatures below 70°F and/or relative humidity below 50% will cause the adhesive to set up more slowly. The installer should monitor the on-site conditions and adjust the open time accordingly.
13. Lay the flooring and rubber underlayment into the wet adhesive. Do not allow the sheet material to "flop" into place; this may cause air entrapment and bubbles beneath the flooring.
14. Immediately roll the floor with a 75–100 lb. roller to ensure proper adhesive transfer. Overlap each pass of the roller by 50% of the previous pass to ensure the floor is properly rolled. Roll the width first and then the length.
15. Fold over the second half of the first roll and half the width of the second roll. Taking roll sizes into account, this will provide an exposed area of substrate of 6 feet wide and 30 feet in length per roll. Spread the adhesive, roll the flooring, and repeat for each consecutive drop.
16. Roll the 5mm rubber underlayment into the adhesive and thoroughly roll with a hand roller
17. Continue the process for each consecutive drop and 4" rubber underlayment. Work at a pace so that you are always folding material back into wet adhesive bed.
18. Let the adhesive cure for several hours before flash coving.
19. Apply Ecore's 4" super floor tape to the 5mm Rubber underlayment filler strip and roll with a hand roller. **DO NOT OVERLAP the 4" Super Floor Tape.**
20. Apply Ecore wall tape on the vertical surface from the 5mm Rubber underlayment edge to the where the finished cap edge will stop. **DO NOT OVERLAP the 4" Wall Tape.**

## INSTALLATION

21. Using a 1-1/4" cove stick for the radius, cut the miter for the outside and inside corners, remove the tape from the wall and floor, and adhere the cove stick.
22. Measure from the Rx cut edge to the top of the cap strip following the radius for the picture frame 2mm Fx flash cove area. Strip a length of Fx material as needed, the width of the fill piece for the perimeter coved areas. Making mitered inside and outside corners.



23. Heat-weld all seams, inside and outside corners with a matching color. Never leave adhesive ridges or puddles. They will telegraph through the material.
24. Do not allow E-Grip III to cure on your hands or the flooring. Immediately wipe off excess adhesive with a rag dampened with mineral spirits! Cured adhesive is very difficult to remove from hands. We strongly suggest wearing gloves while using E-Grip III.
25. Hand roll all seams after the entire floor has been rolled.
26. Keep traffic off the floor for a minimum of 24 hours. Floor should be free from rolling loads for a minimum of 72 hours.



## MAINTENANCE FLOOR CARE FOR Forest Rx

The Forest Rx product incorporates a polyurethane reinforcement, which protects the floor covering by resisting soiling and scuffing. Rubber feet or rubber mats may cause permanent staining to vinyl surfaces. Ecore does not recommend the use of equipment containing rubber feet or rubber backed mats. Combined with the superior closed surface finish, this enhanced protection allows the use of a polish-free maintenance regime. This protection ensures that the intensity of the maintenance and overall cleaning costs are significantly reduced. The following maintenance instructions are designed to maximize the benefits of the PUR, resulting in lower maintenance costs, without compromising the long-term appearance of your floor covering.

### INITIAL CONSTRUCTION CLEAN

1. Remove all loose debris.
2. Ensure that all traces of adhesive are removed from the surface of the floor covering.
3. Mop sweep or vacuum to remove dust and grit.
4. Damp mop with a suitable neutral detergent such as ECF's E-Cleaner.
5. If required, dry buff with a 1000 rpm plus rotary machine fitted with a suitable clean pad

ROUTINE MAINTENANCE - The following recommendations are provided as a guideline, and the frequency can be changed to optimize the appearance.

### DAILY

1. Mop sweep or vacuum to remove dust and loose dirt.
2. If required, spot mop to remove stubborn marks, with a neutral cleanser.

### WEEKLY

1. Assess the appearance of the floor. Undertake the following as required:
2. Light scuffing – dry buff with a 1000 rpm plus rotary machine fitted with a suitable clean pad.  
or
3. Heavier scuffing – spray clean using a floor maintainer and 1000 rpm plus rotary machine fitted with a suitable clean pad.

### PERIODICALLY

1. Assess the appearance of the floor. If the floor has dirt build-up, machine scrub with a scrubber dryer (approx. 165 rpm) fitted with a suitable clean pad, using a neutral or alkaline detergent, as appropriate.
2. Rinse thoroughly and allow to dry.
3. Dry buff to restore finish.
4. The maintenance regime requires the installation of an effective barrier matting system.
5. Cleaners and detergents should be diluted as per the manufacturers' instructions. For recommended products, see the Approved Maintenance Products sheet.
6. Always follow the Health and Safety guidance provided, and dilute cleaners and detergents in accordance with the manufacturers' instructions.
7. Fit protective feet to table and chair legs, to prevent scratching.
8. These maintenance instructions are intended for the PUR Forest Rx floor covering, which has a polyurethane reinforcement.

**NOTE:** In most instances, the above maintenance regime will be sufficient to ensure your floor covering retains the optimum appearance. However where there is no mechanical means of maintaining the floor or should you wish to provide extra protection in heavily trafficked areas, a metalized floor polish should be applied. For further information, contact ECORE Commercial Flooring Technical Support at 800-828-9461. At the date of issue the data presented is correct.

However, ECORE Commercial Flooring reserves the right to make changes which do not adversely affect performance or quality.

**REGULAR CLEANING IS MORE BENEFICIAL TO THE FLOORCOVERING AND MORE COST-EFFECTIVE THAN OCCASIONAL HEAVY CLEANING.**

**Forest Rx APPROVED MAINTENANCE PRODUCTS**

PRODUCT	ECORE Commercial Flooring 877-258-0843 Ecorecommercialflooring.com	Hilway Direct Tel: 1-877-356-6748 www.Hilway.com	PROCHEM Tel 800-241-8180 www.prochem.co.uk	ECOLAB Tel 800-352-5326 www.ecolab.com	Johnson DIVERSEY Tel 800-558-2332 option 5 www.johnsondiversey.com
NEUTRAL CLEANER	E-Cleaner	Neutral Cleaner	Neutra Clean	Oasis 100 or High Performance Neutral Floor Cleaner	Diversey Stride
ALKALINE CLEANER		Allsafe stripper		Maxx Dual Action	Diversey GP Forward
GERMICIDAL CLEANER		Disinfectant Cleaner	Power Pouch Disinfectant	Neutral Disinfectant Cleaner	Diversey J-512 (Food Areas)  Diversey Virex II 256 (non-Food Areas)
MAINTAINER/WASH & WAX		Plus Cleaner/Maintainer		Easy Glow	Diversey Snapback Spray Buff
DRY BRIGHT EMULSION POLISH	E-Finish	High Gloss	Poly Finish	Monostar	Diversey Carefree
SEMI BUFFABLE EMULSION POLISH		Matte Satin High Gloss		Gemstar Laser	Carefree
FULLY BUFFABLE EMULSION POLISH		Matte Satin High Gloss		Gemstar Stratus	High Mileage UHS Floor Finish
POLISH STRIPPER	E-Strip	Allsafe Stripper	Pro Earth floor Strip	Maxx Floor Finish Remover	Diversey Pro Strip SC
POWER CLEANER (SPOT CLEANER)		Turbo Stripper		Maxx Dual Action	Diversey Spitfire

The data presented is correct at the time of printing. However, Ecore Commercial Flooring reserves the right to update this information as and when necessary. For the latest information, please check our web site at [www.Ecorecommercialflooring.com](http://www.Ecorecommercialflooring.com), Providing this information does not imply any equivalence between each of the different manufacturers' products, or that other products would prove unsatisfactory.

## WARRANTY

Ecore Commercial Flooring guarantees our Forest Rx product to be free from defects in workmanship and materials affecting wearing properties, for a period of 5 years from the date of installation, provided that the product has been installed in accordance with the installation instructions issued by us. We guarantee this product to meet all Forest Rx published specifications for a period of 5 years from the date of installation.

Any defect must be notified to us in writing, and we reserve the right to inspect and investigate the defect. If after this investigation we consider the material to be defective, we will supply replacement material free of charge.

This warranty does not cover defects arising from any of the following:

- Excessive moisture
- Chemical Reaction
- Corrosion
- Extremes in temperature
- Abuse
- Abnormal usage above which the product is specified
- Staining or discoloration caused by rubber feet, rubber castors, or rubber backed mats

These warranties are in lieu of any other warranty expressed or implied. Ecore Commercial Flooring shall not be liable for any incidental or consequential damages which may result from a defect. Some states do not allow the exclusion or limitation of incidental or consequential damages, so the above limitation or exclusion may not apply to you. These warranties give you specific rights, and you may also have rights which may vary from state to state. To know what your legal rights are in your state, consult your local or state Consumer Affairs Office or your State Attorney General.



Manufactured in the U.S.A. by:

**ecore**

**715 Fountain Ave – Lancaster, PA 17601**

©2015 All designs and colors are copyrighted by Ecore. ECOsurfaces is a registered trademark of Ecore